

KINTEX
Industries, LLC
 102 Brownfield Drive
 Summerville, South Carolina, 29483

K-DRAIN I
 (Typical Properties)

<u>Property</u>	<u>Test Method</u>	<u>Value</u>
Core Composition		HIPS
Thickness (inches)	ASTM D 1777	1/4
Compressive Strength (psf)	ASTM D 1621	10800
In Plane Flow Rate* (gal/min/ft)	ASTM D 4716	9
Geotextile		
Grab Tensile Strength (lbs)	ASTM D 4632	115
Elongation (%)	ASTM D 4632	> 50
Trap Tear (lbs)	ASTM D 4533	50
Puncture Strength (lbs)	ASTM D 4833	40
Vertical Water Flow (gal/min/sf)	ASTM D 4491	55

* In plane flow tested at 4000 psf and gradient of 0.1

Roll Size: 4' x 104', 416 sf/roll

Telephone: 843-832-6860,
 Email: kintex@knology.net,

Fax: 843-832-5953,
 Cell: 843-343-3401,

Toll Free: 800-626-0454
 Website: www.kintex.net